

DESCRIPTION

- The A-FLEX SEALANT and A-FLEX MESH system is a rubber-based liquid copolymer membrane combined with a polyester spunbonded mesh and mat to seal openings and other joints.

USE

- The liquid applied A-FLEX SEALANT is used in conjunction with the A-FLEX MESH. They are used to seal window and door openings, over expansion joints, where dissimilar substrates meet and anywhere else water infiltration may be of concern. The A-FLEX SEALANT and MESH can be applied over glass-mat sheathing, wood, concrete or masonry, metal, styrene and polyethylene surfaces to form a durable air and weather resistant barrier (WRB) membrane. .

PACKAGING

- A-FLEX SEALANT :
 - 18 Kg (39.6 lb) plastic pail.
 - 4.5 Kg (9.9 lb) pail.
- A-FLEX MESH :
 - Roll length is 54.9 m (180 ft) linear.
 - Roll width: available in 4 or 6 inches.

COVERAGE

	4L container	20L container
4" wide mesh	91 li. m (300 li. ft)	457 li. m (1500 li. ft)
6" wide mesh	61 li. m (200 li. ft)	305 li. m (1000 li. ft)

- Coverage will vary based on the substrate, the job conditions and the individual application techniques.

SURFACE PREPARATION

- A-FLEX SEALANT and MESH system must be installed over an approved substrate or over surfaces that have been specifically designed for the membrane
- Surfaces must be clean, dry, and in good condition, without efflorescence, grease, oil or paint.

MIXING (A-FLEX SEALANT)

- Ready to use.
- All other additives (antifreeze, accelerators, or otherwise) are strictly forbidden.

APPLICATION

- Apply a thin coat of A-FLEX SEALANT using a brush or roller over both sections to be joined and sealed. The use of gloves is recommended. Immediately embed the A-FLEX MESH in the liquid membrane to bridge the gap. A 2 inch overlap of the A-FLEX MESH on the substrate is required. Apply a second coat of A-FLEX SEALANT to fully wet and cover the A-FLEX MESH. For spaces larger than ¼ inch (6 mm), a baker rod is required to fill the gap before the application of the liquid membrane. A third coat is not necessary.

REQUIRED THICKNESS

- Thickness - Wet: 1.32 mm (52 mils).

Vapour Permeability

ASTM E 96-95: Requirement $\geq 170 \text{ ng/Pa}\cdot\text{s}\cdot\text{m}^2$
692 ng/Pa·s·m² ⁽¹⁾

Water Absorption (CCMC)

Requirement $\leq 0,004 \text{ kg}/(\text{m}^2 \text{ s}^{1/2})$
Pass.

Air Permeability

CNB section 5.4.1.2. and ASTM E-283: Requirement $\leq 0.02\text{L}/(\text{s}\cdot\text{m}^2)$
0,00064 L/(s·m²)

(1) The A-FLEX SEALANT membrane does not constitute a vapour barrier.

- Properties
- Test Method
- Result

CLEAN UP

- Immediately wash tools with water while material is still wet. Hardened material will have to be removed physically.

CURING

- Approximately 24 hours under normal climatic conditions.
- Curing time varies according to the temperature and the relative humidity.

LIMITATIONS

- Ambient and surface temperatures must be kept at or above 5 °C (41 °F) for a minimum of 24 hours.
- During installation, minimise the containers' exposure to temperatures over 32 °C (90 °F).
- The A-FLEX SEALANT and MESH must be covered within a maximum period of 30 days

STORAGE

- Protect material from direct sunlight, extreme heat and freezing temperatures.
- Store unused material in tightly sealed containers.

This document contains current information on the product. It is only provided as a guide and is subject to modifications at any time without notice. ADEX Systems Inc. reserves the right to make any modification according to technological progress. Specialised designers, architects, engineers or other professionals that choose to make any use of this information bear the complete responsibility, whatever it be, direct or indirect, that could follow from such use. ADEX Systems Inc. does not bear any responsibility that could give way to damages, defaults, defects, deficiencies, prejudices, loss or decrease of profit, be they direct or indirect, resulting from such use of this information by specialised designers, architects, engineers or other professionals. Please refer to www.adex.ca for the latest version of this document.

April 2014