

DESCRIPTION

- ADEX PARGEX MIX is a pre-blended, ready-to-use coating with the precise GU cement proportions. It is specially designed to parge over concrete foundations and block walls

USE

- ADEX PARGEX MIX is used for parging concrete foundations and blocks. The product can be used above and below grade. The application thickness is 3mm (1/8") to 6mm (1/4") per coat. Pre-blended, ready to use, just add water.

PACKAGING

- 22.7 kg (50 lbs) bag.

COVERAGE

- Approximately 5.6m² (60 ft²) per bag at a thickness of 3mm (1/8 inch).
- Approximately 2.8m² (30 ft²) per bag at a thickness of 6mm (1/4 inch).
- When using as a levelling compound, coverage will vary in relation to the applied thickness.
- Coverage will vary based on the substrate, job conditions and the individual application techniques.

SURFACE PREPARATION

- ADEX PARGEX MIX must be installed on an approved substrate or on a surface that has been specifically designed for its use.
- For direct concrete application, surfaces must be clean and in good condition, without efflorescence, grease, oil or paint. Application over all other surfaces requires a prepared layer of mechanically-fastened galvanized diamond mesh.
- Prior to installation, clean and dampen concrete surfaces with water leaving the surface saturated but free of standing water.
- Protect and mask surrounding areas from accidental contact with ADEX PARGEX MIX.

MIXING

- In a clean container, mix ADEX PARGEX MIX with approximately 4.5 litres (1.2 US gallons) of water.

- Thoroughly mix to a homogenous state. Allow mixture to set up for 5 minutes and mix again to break the initial set.
- Small amounts of water may be added to adjust the consistency and workability. All other additives (antifreeze, accelerators, or otherwise) are strictly forbidden and may void warranties.

APPLICATION

- Apply a 3mm (1/8") to 6mm (1/4") coat of ADEX PARGEX MIX to the prepared surface. Reapply skim coats as required once the initial application is dry.

FINISHING

- Use a wood, plastic, or metal float to render a smooth, homogenous surface.
- For a rougher, textured appearance, allow ADEX PARGEX MIX to partially set; then float the surface to a consistent appearance using a sponge float.

CLEAN UP

- Immediately wash tools with water while material is still wet. Hardened material will have to be removed physically.

CURING

- Approximately 24 hours under normal climatic conditions.
- Curing time is dependent upon the ambient and surface temperatures and the relative humidity.
- Protect from rain and freezing temperatures until fully dry.

STORAGE

- Keep unused materials away from humidity.

SHELF LIFE

- Minimum 12 months.

LIMITATIONS

- Ambient and surface temperatures must be kept at or above 5 °C (41 °F) for a minimum of 24 hours.
- During installation, minimise the containers' exposure to extreme heat (temperatures above 32 °C (90 °F)).

This document contains current information on the product. It is only provided as a guide and is subject to modifications at any time without notice. ADEX Systems Inc. reserves the right to make any modification according to technological progress. Specialised designers, architects, engineers or other professionals that choose to make any use of this information bear the complete responsibility, whatever it be, direct or indirect, that could follow from such use. ADEX Systems Inc. does not bear any responsibility that could give way to damages, defaults, defects, deficiencies, prejudices, loss or decrease of profit, be they direct or indirect, resulting from such use of this information by specialised designers, architects, engineers or other professionals. Please refer to www.adex.ca for the latest version of this document.

November 2019

